

# Charles Cantrill

LIMITED

Grade: CC 2004.



## General information and application.

This is a high compressible material suitable for low and medium bolt pressure, with good flexibility and resilience. The physical characteristics along with oil and fuel resistance make this a qualified material for automotive and industrial gaskets.

This material is also suitable for vibration control in plant rooms etc.

### Material Description

Cork granule size (mm)	1/2
Colour	Black
Binder	Synthetic Rubber

### Physical Characteristics

Density	0.56 – 0.75
Hardness Shore A	55 - 70
Recovery (%)	75
Tensile Strength (kg / cm)	> 80
- Transversal Direction	> 8
- Longitudinal Direction	> 12

### Flexibility

Original (F5)	No cracks
---------------	-----------

### Volume change after immersion

ASTM No 1 Oil 70 Hrs @ 100. C (%)	-5 to +10
ASTM No 3 Oil 70 Hrs @ 100. C (%)	+10 to +40
ASTM Fuel A, 22 Hrs @ 23. C (%)	-2 to +10

Specifications and testing methods according: ASTM 104-93 F229000.